



E6 162

管道短切用合股无捻粗纱

Assembled Roving for Chopping For Pipes


产品说明 Product Description

162 主要用于玻璃钢管道短切成型工艺，该产品采用 E6 玻璃配方，表面涂覆特殊的硅烷基浸润剂，与不饱和聚酯和乙烯基树脂兼容。玻璃钢制品具有良好的耐水性和优良的耐化学腐蚀性。

162 主要用于制造大直径玻璃钢管道。

162 Assembled Roving is coated with a special silane-based sizing compatible with unsaturated polyester and vinyl ester resins. It is produced from our E6 glass formulation.

162 is designed for use in large-diameter FRP chop applications, giving excellent water resistance and chemical corrosion resistance to the FRP products.



产品特点 Product Features

- ◎ 树脂浸透性适中，有良好相容性
- ◎ 在制品中分散均匀，分散性好
- ◎ 具有优异的耐腐蚀性
- ◎ 抗静电性好
- ◎ 切割性好

- Moderate wet-out and good compatibility with resins
- Good dispersion and uniform distribution in parts
- Excellent corrosion resistance
- Good anti-static property
- Good choppability

规格代号 Specification

玻璃类型 Glass type	E6	
浸润剂类型 Sizing type	硅烷 Silane	
典型纤维直径 Typical filament diameter (μm)	13	
典型线密度 Typical linear density (tex)	2400	4800
示例 Example	E6R13-2400-162	

技术指标 Technical Parameters

项目 Item	线密度偏差 Linear density variation	含水率 Moisture content	可燃物含量 Sizing content	硬挺度 Stiffness
单位 Unit	%	%	%	mm
检测方法 Test method	ISO 1889	ISO 3344	ISO 1887	ISO 3375
指标 Standard range	± 4	≤ 0.07	1.20 ± 0.15	125 ± 20

使用说明 Instructions

- ◎ 本产品应在12个月内使用最佳，使用前应保存在原包装内。
- ◎ 产品使用时注意防护，避免产品擦毛、损伤等情况。
- ◎ 使用前调理纱线的温湿度与环境温湿度平衡，使用时对环境温湿度进行适当控制。
- ◎ 刀辊、皮辊做好定期保养。

- The product is best used within 12 months after production, and should be kept in the original package before use.
- Care should be taken when using the product to prevent it from being scratched or damaged.
- The temperature and humidity of the product should be conditioned to be close or equal to the ambient temperature and humidity before use, and the ambient temperature and humidity should be properly controlled during the use.
- The cutter rollers and rubber rollers should be maintained regularly.





E6 162

管道短切用合股无捻粗纱

Assembled Roving for Chopping For Pipes

包装信息 Packaging

项目 Item	单位 unit	指标 Standard			
典型包装方式 Typical packaging method	/	采用托盘包装 Packed on pallets.			
典型纱团高度 Typical package height	mm (in)	260 (10.2)			
纱团内径 Package inner diameter	mm (in)	100 (3.9)			
典型纱团外径 Typical package outer diameter	mm (in)	280 (11.0)		310 (12.2)	
典型纱团重量 Typical package weight	kg (lb)	17 (37.5)		23 (50.7)	
层数 Number of layers	层 (layer)	3	4	3	4
每层纱团个数 Number of packages per layer	个 (pcs)	16		12	
每托纱团个数 Number of packages per pallet	个 (pcs)	48	64	36	48
每托重量 Net weight per pallet	kg (lb)	816 (1799.0)	1088 (2398.6)	828 (1825.4)	1104 (2433.9)
托盘长度 Pallet length	mm (in)	1140 (44.9)		1270 (50.0)	
托盘宽度 Pallet width	mm (in)	1140 (44.9)		960 (37.8)	
托盘高度 Pallet height	mm (in)	940 (37.0)	1200 (47.2)	940 (37.0)	1200 (47.2)



贮存 Storage

在没有特殊要求的情况下，玻璃纤维产品应贮存在干燥、阴凉的地方，防止受潮。最佳存储条件为温度 $-10^{\circ}\text{C} \sim 35^{\circ}\text{C}$ ，相对湿度 $\leq 80\%$ 。为确保安全，避免损坏产品，托盘的堆码高度不应超过三层。当堆放两层或三层高时，要求正确地、平稳地移动上面的托盘。

Unless otherwise specified, the fiberglass products should be stored in a dry, cool and moisture-proof area. The best temperature and humidity should be maintained at $-10^{\circ}\text{C} \sim 35^{\circ}\text{C}$ and $\leq 80\%$ respectively. To ensure safety and avoid damage to the product, the pallets should be stacked not more than three layers high. When the pallets are stacked in two or three layers, special care should be taken to correctly and smoothly move the upper pallet.

安徽天复新材料有限公司 ANHUI TIANFU NEW MATERIAL CO.,LTD

Copyright © 2024 安徽天复新材料有限公司

Add: Room 1716, Lvdi Building, Qianshan Road, Zhengwu District, Hefei City, Anhui Province, China

Tel/WhatsApp/Skype: +86 13696771864

Email: sales@tfcomposite.com

Website: www.tfcomposite.com